

DELTRIN® 527UV black - Stock Shapes (rods, plates, tubes)

Chemical Designation

POM-H (Polyacetal (Homopolymer))

Colour

black

Density

1.41 g/cm³

Fillers

UV stabilizer

Main features

- very good UV and weather resistance
- improved surface hardness
- good machinability
- very good mechanical strength

Target Industries

- automotive industry
- agricultural machinery
- construction industry
- solar systems

<i>Mechanical properties</i>	<i>condition</i>	<i>value</i>	<i>unit</i>	<i>test method</i>	<i>comment</i>
Modulus of elasticity (tensile test)	@ 73 °F	420,000	psi	ASTM D 638	
Tensile strength at yield	@ 73 °F	10,300	psi	ASTM D 638	
Elongation at break (tensile test)	@ 73 °F	15	%	ASTM D 638	
Flexural strength	@ 73 °F	13,500	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F	490,000	psi	ASTM D 790	
Impact strength (Izod)	@ 73 °F	1.25	ft-lbs/in	ASTM D 256	
Rockwell hardness	M Scale	89		ASTM D 785	
Rockwell hardness	R Scale	120		ASTM D 785	
<i>Thermal properties</i>	<i>condition</i>	<i>value</i>	<i>unit</i>	<i>test method</i>	<i>comment</i>
Melting temperature		352	°F	-	1) (1) Injection molded data
Deflection temperature	@ 66 psi	325	°F	ASTM D 648	2) (2) Injection molded data
Deflection temperature	@ 264 psi	198	°F	-	3) (3) Injection molded data
Service temperature	Long Term	185	°F	-	4) (4) Injection molded data
Thermal expansion (CLTE)		6.1*10 ⁻⁵	in/in/°F	-	5) (5) Injection molded data
<i>Other properties</i>	<i>condition</i>	<i>value</i>	<i>unit</i>	<i>test method</i>	<i>comment</i>
Moisture absorption	@ 24 hrs, 73 °F	0.14	%	ASTM D 570	(1) Data obtained from public source
Flammability (UL94)		HB		-	1)

→ Resin specification:
ASTM D6778-06 POM0132 superseding ASTM D4181-00 POM132
Shapes specification:
ASTM D6100 POM01601222434

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.