

TECAFLON® PVDF natural - Stock Shapes (rods, plates, tubes)

Chemical Designation

PVDF (Polyvinylidene fluoride)

Colour

white

Density

1.78 g/cm³

Main features

- excellent chemical resistance
- inherent flame resistance
- high gamma radiation resistance
- good UV and weather resistance
- good mechanical properties
- low moisture absorption
- good machinability

Target Industries

- chemical plant engineering
- process engineering
- medical technology
- cleanroom technology
- food processing
- food engineering

<i>Mechanical properties</i>	<i>condition</i>	<i>value</i>	<i>unit</i>	<i>test method</i>	<i>comment</i>
Modulus of elasticity (tensile test)	@ 73 °F	350,000	psi	ASTM D 638	
Tensile strength at yield	@ 73 °F	8,100	psi	ASTM D 638	
Tensile strength at break	@ 73 °F	7,800	psi	ASTM D 638	
Elongation at break (tensile test)	@ 73 °F	35	%	ASTM D 638	
Flexural strength	@ 73 °F	9,700	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F	320,000	psi	ASTM D 790	
Compression strength	@ 73 °F, 10% strain	11,600	psi	ASTM D 695	
Compression	@ 73 °F, 1% strain	3,200	psi	ASTM D 695	
Compression modulus	@ 73 °F	160,000	psi	ASTM D 695	
Impact strength (Izod)	@ 73 °F	2.49	ft-lbs/in	ASTM D 256	
Rockwell hardness	@ 73 °F, M scale	79		ASTM D 785	
<i>Thermal properties</i>	<i>condition</i>	<i>value</i>	<i>unit</i>	<i>test method</i>	<i>comment</i>
Melting temperature		346	°F	ASTM D 3418	(1) publicly sourced data
Deflection temperature	@264 psi	235	°F	ASTM D 648	(2) Injection molded samples (3) Data obtained from public source
Deflection temperature	@ 66 psi	300	°F	ASTM D 648	(4) Data obtained from public source
Service temperature	short term	300	°F	-	(5) publicly sourced data
Service temperature	Long Term	300	°F	-	(6) publicly sourced data
Thermal expansion (CLTE)		7.1*10 ⁻⁵	in/in/°F	ASTM D 696	
Thermal conductivity		1.32	BTU-in/hr-ft ² -°F	ASTM C 177	
<i>Electrical properties</i>	<i>condition</i>	<i>value</i>	<i>unit</i>	<i>test method</i>	<i>comment</i>
volume resistance	@ 73 °F	5*10 ¹⁴	Ω*cm	ASTM D 257	(1) publicly sourced data
Dielectric strength		510	V/mil	ASTM D 149	(2) Injection molded samples
Dissipation factor	@ 60 Hz, 73 °F	0.06		ASTM D 150	(3) publicly sourced data
Dielectric constant	@ 60 Hz, 73 °F, 50% RH	9		ASTM D 150	(4) publicly sourced data
<i>Other properties</i>	<i>condition</i>	<i>value</i>	<i>unit</i>	<i>test method</i>	<i>comment</i>
Moisture absorption	@ 24 hrs, 73 °F	0.02	%	ASTM D 570	(1) Thickness greater than 0.1 mm Injection molded samples
Flammability (UL94)		V0		-	

→ Resin specification:
ASTM D3222-05 (Reapproved 2015) Type II
Shapes specification:
ASTM D 6713-14 S-PVDF0111

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.