

TECARAN ABS natural - Stock Shapes (rods, plates, tubes)

Chemical Designation

ABS (Acrylonitrile-butadiene-styrene copolymer)

Colour

beige opaque

Density

1.02 g/cm³

Main features

- electrically insulating
- high stiffness
- good chemical resistance
- low density
- good damping
- high toughness
- low moisture absorption

Target Industries

- food processing
- home appliances
- automotive industry
- fixture construction
- food engineering
- electronics
- medical technology

Mechanical properties	condition	value	unit	test method	comment
Modulus of elasticity (tensile test)	@ 73 °F	400,000	psi	ASTM D 638	(1) Injection molded data (2) Injection molded data (3) Injection molded data
Tensile strength at yield	@ 73 °F	5,800	psi	ASTM D 638	
Tensile strength at break	@ 73 °F	4,000	psi	ASTM D 638	
Elongation at yield (tensile test)	@ 73 °F	2.0	%	ASTM D 638	
Elongation at break (tensile test)	@ 73 °F	30	%	ASTM D 638	
Flexural strength	@ 73 °F	8,900	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F	310,000	psi	ASTM D 790	
Compression strength	@ 73 °F, 1% strain	3,200	psi	ASTM D 695	
Compression strength	@ 73 °F, 10% strain	7,100	psi	ASTM D 695	
Compression modulus	@ 73 °F	375,000	psi	ASTM D 695	
Impact strength (Izod)	@ 73 °F	5.3	ft-lbs/in	ASTM D 256	
Rockwell hardness	@ 73 °F R Scale	108		ASTM D 785	
Shore hardness	@ 73 °F D scale	78		ASTM D 2240	
Coefficient of friction	Static	0.19 - 0.21		ASTM D 3702	1)
Coefficient of friction	Dynamic, 40 psi, 50 fpm	0.35		ASTM D 3702	2)
Wear (K) factor	Against Steel, 40 psi, 50 fpm	3500*10 ⁻¹⁰	in ³ -min/ft-lbs-hr	ASTM D 3702	3)
Thermal properties	condition	value	unit	test method	comment
Vicat softening point		224	°F	-	1) (1) Injection molded data (2) Injection molded data (3) Injection molded data (4) per UL746B (5) Injection molded data
Glass transition temperature		220	°F	ASTM D 3418	
Deflection temperature	@ 66 psi	200	°F	ASTM D 648	2)
Deflection temperature	@264 psi	177	°F	ASTM D 648	3)
Service temperature	Intermittent	210	°F	-	
Service temperature	Long Term	160	°F	-	4)
Thermal expansion (CLTE)	-40F to 100F	5.6*10 ⁻⁵	in/in/°F	ASTM D 696	5)
Electrical properties	condition	value	unit	test method	comment
surface resistivity		1.0*10 ¹⁴	Ω/square	ASTM D 257	1) (1) Data obtained from public source (2) Injection molded data (3) Injection molded data (4) Injection molded data (5) Injection molded data
volume resistance		1*10 ¹⁵	Ω*cm	ASTM D 257	2)
Dielectric strength		450	V/mil	ASTM D 149	3)
Dissipation factor	@ 60 Hz, 73 °F	0.02		ASTM D 150	4)
Dielectric constant	@ 60 Hz, 73 °F, 50% RH	3.3		ASTM D 150	5)
Other properties	condition	value	unit	test method	comment
Moisture absorption	@ 24 hrs, 73 °F	0.13	%	ASTM D 570	(1) Injection molded data (1.5mm thick)
Moisture absorption	@ saturation, 73 °F	0.70	%	ASTM D 570	
Flammability (UL94)		HB		-	1)

→ Resin specification:
ASTM D4673-02 (Reapproved 2008) ABS220B44500
Shapes specification:
NONE

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.