

TECAMID® 66 HI natural - Stock Shapes (rods, plates, tubes)

Chemical Designation

PA 66 (Polyamide 66)

Colour

natural opaque

Density

1.15 g/cm³

Main features

- heat stabilized
- low thermal expansion
- good mechanical properties
- good dimensional stability

Target Industries

- conveyor technology
- heavy duty industry
- mechanical engineering
- power engineering

<i>Mechanical properties</i>	<i>condition</i>	<i>value</i>	<i>unit</i>	<i>test method</i>	<i>comment</i>
Modulus of elasticity (tensile test)	@ 73 °F	350,000	psi	ASTM D 638	
Tensile strength at yield	@ 73 °F	10,000	psi	ASTM D 638	
Elongation at break (tensile test)	@ 73 °F	25	%	ASTM D 638	
Modulus of elasticity (flexural test)	@ 73 °F	440,000	psi	ASTM D 790	
Impact strength (Izod)	@ 73 °F	1.2	ft-lbs/in	ASTM D 256	
<i>Thermal properties</i>	<i>condition</i>	<i>value</i>	<i>unit</i>	<i>test method</i>	<i>comment</i>
Melting temperature		504	°F	ASTM D 2133	(1) Data obtained from public source
Deflection temperature	@ 66 psi	392	°F	ASTM D 648	1) (2) Data obtained from public source
Deflection temperature	@264 psi	194	°F	ASTM D 648	2) (3) Data obtained from public source
Service temperature	Long Term	185	°F	-	3)
<i>Other properties</i>	<i>condition</i>	<i>value</i>	<i>unit</i>	<i>test method</i>	<i>comment</i>
Moisture absorption	@24 hr, 73 °F	0.275	%	ASTM D 570	(1) 0.75 mm
Flammability (UL94)		HB	-	-	1)

- Resin specification:
ASTM D6779-11 PA0124
- Shapes specification:
ASTM D5989-11 S-PA0131

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.

Ensinger Inc. Headquarters
365 Meadowlands Boulevard
Washington, PA 15301, USA

Phone 800-243-3221 Sales
Phone 800-869-4029 Technical
Fax 724-746-9209
sales@ensingerusa.com

Date: 2019/01/14

Version: A0