

## TECAFIL PA6 GF30 black - 2.85 mm - Filament

### Chemical Designation

PA 6 (Polyamide 6)

### Colour

black opaque

### Density

1.36 g/cm<sup>3</sup> (\*2)

### Fillers

glass fibres, 30% glass fibres

### Main features

- high strength
- high dimensional stability
- good weldable and bondable
- good heat deflection temperature
- resistant to many oils, greases and fuels

### Target Industries

- electronics
- automotive industry
- mechanical engineering

General material information	parameter	value	unit	norm	comment
Diameter		2,85 +/- 0,05	mm	-	
Spool measurements	outer diameter	Ø 200	mm	-	1)
Spool measurements	holder	Ø 52	mm	-	
Spool measurements	width	55	mm	-	
Spool Material		Polycarbonate		-	2)
Filament Load per Spool		750	g	-	
Filament Length per Spool		83	m	-	3)
Mechanical properties	parameter	value	unit	norm	comment
Tensile strength	5mm/min, Orientation XY	72	MPa	DIN EN ISO 527-2	1) (1) (*5), (*6) (2) (*5), (*6)
Modulus of elasticity (tensile test)	5mm/min, Orientation XY	5200	MPa	DIN EN ISO 527-2	2) (3) (*5), (*6) (4) (*5), (*6)
Elongation at break (tensile test)	5mm/min, Orientation XY	5,0	%	DIN EN ISO 527-2	3) (5) (*5), (*6) (6) (*5), (*6)
Flexural strength	2mm/min, Orientation XY	115	MPa	DIN EN ISO 178	4)
Modulus of elasticity (flexural test)	2mm/min, Orientation XY	4460	MPa	DIN EN ISO 178	5)
Elongation at break (flexural test)	2mm/min, Orientation XY	6,0	%	DIN EN ISO 178	6)
Thermal properties	parameter	value	unit	norm	comment
Glass transition temperature		60	°C	ASTM D 3418	1) (1) (*2) (2) (*2)
Melting temperature		220	°C	DIN EN ISO 11357	2) (3) (*2)
Deflection temperature	HDT-A	210	°C	ISO-R 75 Method A	3) (4) (*2) (5) (*2)
Service temperature	short term	180	°C	-	4) (6) (*2)
Service temperature	long term	100	°C	-	5)
Thermal expansion (CLTE)		6	10 <sup>-5</sup> K <sup>-1</sup>	DIN EN ISO 11359-1;2	6)
Other properties	parameter	value	unit	norm	comment
Moisture absorption		0,3	%	DIN EN ISO 62	1) (1) (*2) (2) (*2)
Melt flow index (MFI)		-	g/10 min	DIN EN ISO 1133	2)
Processing parameter	parameter	value	unit	norm	comment
Nozzle temperature		260 - 290	°C	-	(1) not required
Max. melt temperature		300	°C	-	
Print bed temperature		80 - 140	°C	-	
Build chamber temperature		80 - 100	°C	-	1)
Nozzle diameter		0,4 - 0,6	mm	-	
Print speed		30 - 50	mm/s	-	
Fan speed		0	%	-	
Predrying	parameter	value	unit	norm	comment
Drying temperature		80	°C	-	1) (1) (*4)
Drying time		8	h	-	

→ To achieve optimum mechanical properties, it is recommended to pre-dry the material with the above mentioned parameters.

- (\*1) Values measured on injection moulded test specimens
- (\*2) Values measured on the raw material
- (\*3) The exact parameters depend on the printer used.
- (\*4) Do not exceed maximum drying temperature of 120°C
- (\*5) Properties tested on printed specimens
- (\*6) Specimens printed on Ultimaker S5

→ The filament should preferably be stored in dry, normal temperature rooms and protected from direct sunlight.

Our information and statements reflect to current state of our knowledge and shall inform about the products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at [ensingerplastics.com](http://ensingerplastics.com). Technical changes reserved. European-made or imported varieties comply with REACH Regulation 1907/2006 / EC as amended Unless otherwise noted, these values were determined by tests on injection moulded samples, dry as moulded. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. In order to achieve optimum mechanical properties, pre-drying of the material is recommended with the parameters mentioned above. Filaments should preferably be stored in dry rooms at normal temperatures and be protected from direct sunlight.