

TECAFIL PC FR natural - 2.85 mm - Filament

Chemical Designation

PC (Polycarbonate)

Colour

natural transparent

Density

1.23 g/cm³ (*2)

Fillers

flame retardant (halogen free)

Main features

- electrically insulating
- good weldable and bondable
- tested according to EN 45545
- flame retardant as per FAR 25.853
- flame retardant according to UL94 V-0

Target Industries

- electronics
- Railway Interiors
- automotive industry
- mechanical engineering
- aircraft and aerospace interiors
- aircraft and aerospace technology

General material information	parameter	value	unit	norm	comment
Diameter		2,85 +/- 0,05	mm	-	(1) standard spool body (2) Ø 2,85mm
Spool measurements	outer diameter	Ø 200	mm	-	1)
Spool measurements	width	55	mm	-	
Spool measurements	holder	Ø 52	mm	-	
Spool Material		Polycarbonate		-	
Filament Load per Spool		750	g	-	
Filament Length per Spool		92	m	-	2)

Mechanical properties	parameter	value	unit	norm	comment
Tensile strength	5mm/min, Orientation XY	69	MPa	DIN EN ISO 527-2	1) (1) (*5), (*6) (2) (*5), (*6)
Tensile strength	5mm/min, Orientation ZX	34	MPa	DIN EN ISO 527-2	2) (3) (*5), (*6) (4) (*5), (*6)
Modulus of elasticity (tensile test)	5mm/min, Orientation XY	2750	MPa	DIN EN ISO 527-2	3) (5) (*5), (*6) (6) (*5), (*6)
Modulus of elasticity (tensile test)	5mm/min, Orientation ZX	2800	MPa	DIN EN ISO 527-2	4) (7) (*5), (*6) (8) (*5), (*6) (9) (*5), (*6)
Elongation at break (tensile test)	5mm/min, Orientation XY	3,8	%	DIN EN ISO 527-2	5) (10) (*5), (*6) (11) (*5), (*6)
Elongation at break (tensile test)	5mm/min, Orientation ZX	1,4	%	DIN EN ISO 527-2	6) (12) (*5), (*6)
Flexural strength	5mm/min, Orientation XY	105	MPa	DIN EN ISO 178	7)
Flexural strength	5mm/min, Orientation ZX	67	MPa	DIN EN ISO 178	8)
Modulus of elasticity (flexural test)	5mm/min, Orientation XY	2750	MPa	DIN EN ISO 178	9)
Modulus of elasticity (flexural test)	5mm/min, Orientation ZX	3300	MPa	DIN EN ISO 178	10)
Elongation at break (flexural test)	5mm/min, Orientation XY	3,9	%	DIN EN ISO 178	11)
Elongation at break (flexural test)	5mm/min, Orientation ZX	1,8	%	DIN EN ISO 178	12)

Thermal properties	parameter	value	unit	norm	comment
Glass transition temperature		80	°C	ASTM D 3418	1) (1) (*2) (2) (*2)
Melting temperature		-		DIN EN ISO 11357	2) (3) (*5), (*6) (4) (*2)
Deflection temperature	HDT-A	69	°C	ISO-R 75 Method A	3) (5) (*2) (6) (*2)
Service temperature	short term	70	°C	-	4)
Service temperature	long term	60	°C	-	5)
Thermal expansion (CLTE)		-	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2	6)

Other properties	parameter	value	unit	norm	comment
Moisture absorption		0,14	%	DIN EN ISO 62	(1) (*5), (*6) (2) (*5), (*6)
Flammability (UL94)	125x13x1,5mm; Orientation XY	V0		DIN IEC 60695-11-10;	1) (3) (*5), (*6) (4) (*5), (*6)
Flammability (UL94)	125x13x5,0mm; Orientation XY	V0		DIN IEC 60695-11-10;	2) (5) (*5), (*6) (6) (*5), (*6) (7) (*5), (*6)
Flammability	s=1,5mm & s=10mm	R22 HL3, R23 HL3,		EN 45545-2:2016	3)
Flammability	60 sec. Vertical Bunsen Burner test, FAR §25.853 (a) and Appendix F, Part I, para. (a)(1)(i)	1,5	mm	FAR 25.853	4)
Flammability	12 sec. Vertical Bunsen Burner test, FAR §25.853 (a) and Appendix F, Part I, para. (a)(1)(ii)	1,5	mm	FAR 25.853	5)
Flammability	15 sec. Horizontal Bunsen Burner test, FAR §25.853 (a) and Appendix F, Part I, para. (a)(1)(iv)& (v)	1,5	mm	FAR 25.853	6)
Flammability	Gas Toxicity, as per Boeing BSS 7239	1,5	mm	-	7)

Processing parameter	parameter	value	unit	norm	comment
Nozzle temperature		240 - 280	°C	-	(1) not required
Max. melt temperature		300	°C	-	
Print bed temperature		70 - 90	°C	-	

Build chamber temperature	-	-	1)
Nozzle diameter	0,4	mm	-
Print speed	30 - 50	mm/s	-
Fan speed	20 - 40	%	-

<i>Predrying</i>	<i>parameter</i>	<i>value</i>	<i>unit</i>	<i>norm</i>	<i>comment</i>
Drying temperature		60	°C	-	1) (1) (*4)
Drying time		8	h	-	

→ To achieve optimum mechanical properties, it is recommended to pre-dry the material with the above mentioned parameters.

- (*1) Values measured on injection moulded test specimens
- (*2) Values measured on the raw material
- (*3) The exact parameters depend on the printer used.
- (*4) Do not exceed maximum drying temperature of 120°C
- (*5) Properties tested on printed specimens
- (*6) Specimens printed on Ultimaker S5

→ The filament should preferably be stored in dry, normal temperature rooms and protected from direct sunlight.

Our information and statements reflect to current state of our knowledge and shall inform about the products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at ensingerplastics.com. Technical changes reserved. European-made or imported varieties comply with REACH Regulation 1907/2006 / EC as amended Unless otherwise noted, these values were determined by tests on injection moulded samples, dry as moulded. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. In order to achieve optimum mechanical properties, pre-drying of the material is recommended with the parameters mentioned above Filaments should preferably be stored in dry rooms at normal temperatures and be protected from direct sunlight.

Ensinger GmbH
Rudolf-Diesel Str. 8
71154 Nürtingen - Deutschland

Tel +49 7032 819 0
Fax +49 7032 819 100
ensingerplastics.com

Date: 2024/06/26

Version: AE