

TECAMID 66 GF35 black - 型材 (棒材, 板材, 管件)

化學命名

PA 66 (聚醯胺 66)

顏色

黑色 不透明

密度

1.4 g/cm³

添加物

玻璃纖維

加工後所產生的數據(依德國標準氣候為主)。

主要特色

- 極高的剛性
- 耐油、潤滑油及燃油
- 良好的磨損性
- 極高的強度
- 良好的尺寸穩定性
- 良好的熱變形溫度
- 良好的可焊接性和黏結性

目標產業

- 航空與航太科技
- 機械工程

機械特性	參數	值	單位	標準	註解
抗拉強度	50mm/min	98	MPa	DIN EN ISO 527-2	(1) For tensile test: specimen type 1b
彈性模數 (張力測試)	1mm/min	5700	MPa	DIN EN ISO 527-2	1)
降伏點伸長率	50mm/min	7	%	DIN EN ISO 527-2	
斷裂伸長率	50mm/min	11	%	DIN EN ISO 527-2	
抗彎強度		149	MPa	DIN EN ISO 178	
彈性模數 (彎曲測試)		5100	MPa	DIN EN ISO 178	
衝擊強度(Charpy)		80	kJ/m ²	DIN EN ISO 179-1eU	
缺口衝擊強度(Charpy)		5	kJ/m ²	DIN EN ISO 179-1eA	
蕭氏硬度	D	84		DIN EN ISO 868	
熱特性	參數	值	單位	標準	註解
玻璃轉化溫度		48	°C	DIN EN ISO 11357	1)
熔化溫度		254	°C	DIN EN ISO 11357	(1) Found in public sources. (2) Found in public sources. Individual testing regarding application conditions is mandatory.
使用溫度	short term	170	°C		2)
使用溫度	long term	110	°C		
電性特性	參數	值	單位	標準	註解
表面電阻	Silver electrode, 23°C, 12% r.h.	10 ¹⁴	Ω	-	(1) Due to moisture uptake of the material the electrical insulation properties cannot be 100% guaranteed, despite single measurements suggesting otherwise.
體積電阻	Silver electrode, 23°C, 12% r.h.	10 ¹⁴	Ω*cm	-	1)
其他特性	參數	值	單位	標準	註解
耐熱水/鹼		(+)		-	1)
耐候性		(+)		-	(1) (+) limited resistance (2) Corresponding means no listing at UL (yellow card). The information might be taken from resin, stock shape or estimation. Individual testing regarding application conditions is mandatory.
耐燃性(UL94)	corresponding to	HB		DIN IEC 60695-11-10;	2)

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions (typically rods with diameter 40-60 mm according to DIN EN 15860) on extruded and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com. Technical changes reserved.