

# TECAMID 6 GF30 black - Stock Shapes (rods, plates, tubes)

## Chemical Designation

PA 6 (Polyamide 6)

## Colour

black opaque

## Density

1.36 g/cm<sup>3</sup>

## Fillers

glass fibres

Data generated directly after machining (standard climate Germany).

## Main features

- very high strength
- resistant to many oils, greases and fuels
- good wear properties
- good weldable and bondable
- high dimensional stability
- good heat deflection temperature
- good machinability

## Target Industries

- mechanical engineering
- electronics
- automotive industry

Mechanical properties	parameter	value	unit	norm	comment
Tensile strength	50mm/min	98	MPa	DIN EN ISO 527-2	(1) For tensile test: specimen type 1b
Modulus of elasticity (tensile test)	1mm/min	5700	MPa	DIN EN ISO 527-2	(1) (2) For flexural test: support span 64mm, norm specimen.
Tensile strength at yield	50mm/min	98	MPa	DIN EN ISO 527-2	(3) Specimen 10x10x10mm
Elongation at yield (tensile test)	50mm/min	4	%	DIN EN ISO 527-2	(4) Specimen 10x10x50mm, modulus range between 0.5 and 1% compression.
Elongation at break (tensile test)	50mm/min	5	%	DIN EN ISO 527-2	(5) For Charpy test: support span 64mm, norm specimen.
Flexural strength	2mm/min, 10 N	140	MPa	DIN EN ISO 178	(2)
Modulus of elasticity (flexural test)	2mm/min, 10 N	5200	MPa	DIN EN ISO 178	
Compression strength	1% / 2% / 5% 5mm/min, 10 N	21/42/107	MPa	EN ISO 604	(3)
Compression modulus	5mm/min, 10 N	4200	MPa	EN ISO 604	(4)
Impact strength (Charpy)	max. 7,5J	60	kJ/m <sup>2</sup>	DIN EN ISO 179-1eU	(5)
Shore hardness	D	84		DIN EN ISO 868	
Thermal properties	parameter	value	unit	norm	comment
Glass transition temperature		49	°C	DIN EN ISO 11357	(1)
Melting temperature		218	°C	DIN EN ISO 11357	(2)
Service temperature	short term	180	°C		(2)
Service temperature	long term	100	°C		
Thermal expansion (CLTE)	23-60°C, long.	6	10 <sup>-5</sup> K <sup>-1</sup>	DIN EN ISO 11359-1;2	
Thermal expansion (CLTE)	23-100°C, long.	6	10 <sup>-5</sup> K <sup>-1</sup>	DIN EN ISO 11359-1;2	
Specific heat		1.3	J/(g*K)	ISO 22007-4:2008	
Thermal conductivity		0.41	W/(K*m)	ISO 22007-4:2008	
Electrical properties	parameter	value	unit	norm	comment
surface resistivity	Silver electrode, 23°C, 12% r.h.	10 <sup>14</sup>	Ω	-	(1) Specimen in 20mm thickness
volume resistivity	Silver electrode, 23°C, 12% r.h.	10 <sup>14</sup>	Ω*cm	-	(2) Due to the black colourant and moisture uptake of the material the electrical
Dielectric strength	23°C, 50% r.h.	32	kV/mm	ISO 60243-1	(3) insulation properties cannot be 100% guaranteed, despite single measurements suggesting otherwise.
Resistance to tracking (CTI)	Platin electrode, 23°C, 50% r.h., solvent A	550 / 475	V	DIN EN 60112	(3) Specimen in 1mm thickness
Other properties	parameter	value	unit	norm	comment
Water absorption	24h / 96h (23°C)	0.2 / 0.3	%	DIN EN ISO 62	(1) Ø ca. 50mm, h=13mm
Resistance to hot water/ bases		(+)		-	(2) (+) limited resistance
Resistance to weathering		(+)			(3) Corresponding means no listing at UL (yellow card). The information might be taken from resin, stock shape or estimation. Individual testing regarding application conditions is mandatory.
Flammability (UL94)	corresponding to	HB		DIN IEC 60695-11-10;	(3)

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions (typically rods with diameter 40-60 mm according to DIN EN 15860) on extruded and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at [www.ensingerplastics.com](http://www.ensingerplastics.com). Technical changes reserved.