

TECANAT® GF20 natural - Stock Shapes (rods, plates, tubes)

Chemical Designation

PC (Polycarbonate)

Colour

blue grey opaque

Density

1.33 g/cm³

Fillers

glass fibres

Main features

- high toughness
- good thermal stability
- very high stiffness
- good tensile strength

Target Industries

- aircraft and aerospace technology
- automotive industry
- fixture construction
- electrical engineering
- mechanical engineering

Mechanical properties	condition	value	unit	test method	comment
Modulus of elasticity (tensile test)	@ 73 °F	700,000	psi	ASTM D 638	(1) Data obtained from public source
Tensile strength at yield	@ 73 °F	11,000	psi	ASTM D 638	(2) Injection molded data
Elongation at break (tensile test)	@ 73 °F	3	%	ASTM D 638	(3) Injection molded data
Flexural strength	@ 73 °F	16,700	psi	ASTM D 790	(4) Injection molded data
Modulus of elasticity (flexural test)	@ 73 °F	600,000	psi	ASTM D 790	
Compression strength	@ 73 °F, 1% strain	2,000	psi	ASTM D 695	
Compression strength	@ 73 °F, 10% strain	15,000	psi	ASTM D 695	
Compression modulus	@ 73 °F	319,000	psi	ASTM D 695	
Impact strength (Izod)	@ 73 °F	2.06	ft-lbs/in	-	1)
Rockwell hardness	@ 73 °F M Scale	87		ASTM D 785	2)
Coefficient of friction	Dynamic, 40 psi, 50 fpm	0.22		ASTM D 3702	3)
Wear (K) factor	Against Steel, 40 psi, 50 fpm	120*10 ⁻¹⁰	in ³ -min/ft-lbs-hr	ASTM D 3702	4)
Thermal properties	condition	value	unit	test method	comment
Vicat softening point		329	°F	ASTM D 1525	1)
Deflection temperature	@264 psi	295	°F	ASTM D 648	2)
Deflection temperature	@ 66 psi	298	°F	ASTM D 648	3)
Service temperature	Intermittent	275	°F	-	4)
Service temperature	Long Term	266	°F	-	5)
Thermal expansion (CLTE)	-40 F to 203 F	1.5	*10 ⁻⁵ in/in/°F	ASTM E 831	
Electrical properties	condition	value	unit	test method	comment
volume resistance		1.0*10 ¹⁷	Ω*cm	ASTM D 257	1)
Dielectric strength		490	V/mil	ASTM D 149	2)
Dissipation factor	@ 60 Hz, 73 °F	0.0009		ASTM D 150	3)
Dielectric constant	@ 60 Hz, 73 °F, 50% RH	3.17	%	ASTM D 150	4)
Dielectric constant	1 MHz	3.13	%	ASTM D 150	5)
Other properties	condition	value	unit	test method	comment
Moisture absorption	@ saturation, 73 °F	0.29	%	ASTM D 570	1)
Moisture absorption	@ 24 hrs, 73 °F	0.07	%	ASTM D 570	2)
Flammability (UL94)		V0		-	3)

→ Resin specification:
ASTM D 3935-09 PC0120G20A33230
Shapes specification:
ASTM D6098-10 S-PC0100G2010000000

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.