

TECANYL VH2 black - 型材 (棒材, 板材, 管件)

化學命名

PPE (聚苯醚)

顏色

黑色 不透明

密度

1.1 g/cm³

添加物

阻燃劑 (無鹵素)

主要特色

- 根據FAR 25.853 防火測試
- 絕佳的尺寸穩定性
- 優異的耐化學性
- 根據UL94 V-0 耐燃測試
- 低煙排放
- 低吸濕性
- 良好的電絕緣性

目標產業

- 航空與航太內裝
- 航空與航太科技
- 鐵路內裝
- 運輸工具

機械特性	參數	值	單位	標準	註解
抗拉強度	50 mm/min	57	MPa	DIN EN ISO 527-2	(1) For tensile test: specimen type 1b
彈性模數 (張力測試)	1mm/min	2300	MPa	DIN EN ISO 527-2	(1) (2) For flexural test: support span 64mm, norm specimen.
降伏點抗拉強度	50mm/min	57	MPa	DIN EN ISO 527-2	(3) Specimen 10x10x10mm
降伏點伸長率	50mm/min	11	%	DIN EN ISO 527-2	(4) Specimen 10x10x50mm, modulus range between 0.5 and 1% compression.
斷裂伸長率	50mm/min	20	%	DIN EN ISO 527-2	(5) For Charpy test: support span 64mm, norm specimen.
抗彎強度	2mm/min, 10 N	96	MPa	DIN EN ISO 178	(2) (6) Specimen in 4mm thickness
彈性模數 (彎曲測試)	2mm/min, 10 N	2100	MPa	DIN EN ISO 178	
壓縮強度	1% / 2% / 5%	19/34/77	MPa	EN ISO 604	(3)
壓縮模數	5mm/min	1300	MPa	EN ISO 604	(4)
衝擊強度(Charpy)	max. 7.5J	91	kJ/m ²	DIN EN ISO 179-1eU	(5)
缺口衝擊強度(Charpy)	max. 7.5J	16	%	DIN EN ISO 179-1eA	
球壓式硬度		143	MPa	ISO 2039-1	(6)
熱特性	參數	值	單位	標準	註解
玻璃轉化溫度		152	°C	DIN EN ISO 11357	(1) Found in public sources. Individual testing regarding application conditions is mandatory.
使用溫度	long term	85	°C	-	
使用溫度	short term	110	°C	-	(1)
熱膨脹 (CLTE)	23-60°C, longitudinal	8,1	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2	
熱膨脹 (CLTE)	23-100°C, longitudinal	8,1	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2	
其他特性	參數	值	單位	標準	註解
吸水率	24h / 96h (23°C)	0.08/0.15	%	DIN EN ISO 62	(1) ASTM Test Method 60695-2
耐燃性	Glow Wire Ignitability Temp, 3.0 mm	800	°C	-	(1) (2) ASTM Test Method 60695-2
耐燃性	Glow Wire Ignitability Temp, 2.0 mm	775	°C	-	(2) (3) ASTM Test Method 60695-2
耐燃性	Glow Wire Ignitability Temp, 1.5 mm	775	°C	-	(3) (4) ASTM Test Method 60695-2
耐燃性	Glow Wire Ignitability Temp, 1.0 mm	775	°C	-	(4) (5) Units: 1.5 mm (6) ASTM Test Method 60695-2
耐燃性(UL94)		V0	-	-	(7) passed, 3 mm specimen (8) passed, FAA Smoke Density Test (resin data)
耐燃性	Glow Wire Flammability Index 960°C passes @	1.0	mm	-	(6) (9) passed, Toxicity - Draeger Tube (resin data)
耐燃性	60 sec. Vertical Bunsen Burner test FAR 25.853 Appx F, Prt 1, (a), 1, (Air)	+	-	FAR 25.853	(7) (10) Flame Spread Index (11) passed, FAR 25.853 (12) passed, FAR 25.853
耐燃性	FAR 25.853 Appx F, Prt 1, (a), 1, (Air)	+	-	FAR 25.853	(8)
耐燃性	FAR 25.853 Appx F, Prt 1, (a), 1, (Air)	+	-	-	(9)
耐燃性	ASTM E 162 (rail)	~15	-	-	(10)
耐燃性	ASTM E 662 (Air/Rail) Ds @ 1.5 min	11-13	-	-	(11)
耐燃性	ASTM E 662 (Air/Rail) Ds @ 4.0 min	20-40	-	-	(12)

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensinger-inc.com.