

TECARIM 1500 yellow - Halvfabrikata

Kemisk betegnelse

PA 6 C (Støbt Polyamid 6)

Farve

gul uigenomsigtig

1.11 g/cm³

Fillers

elastomer

Vigtigste egenskaber

- elektrisk isolerende
- resistent overfor mange olier, fedt og brændstoffer
- høj sejhed
- gode glid- og slidegenskaber
- gode slidegenskaber
- god slagstyrke

Målsegmenter

- Bilindustrien
- mekanisk industri
- heavy duty industri

Data genereret direkte efter bearbejdning (standard klima, Tyskland)

Mekaniske egenskaber	parameter	værdi	enhed	norm	kommentar
Trækstyrke	50mm/min	53	MPa	DIN EN ISO 527-2	(1) For tensile test: specimen type 1b
Elasticitetsmodul (tensile test)	1mm/min	2200	MPa	DIN EN ISO 527-2	1) (2) For flexural test: support span 64mm, norm specimen.
Trækforsøg -Forlængelse ved brud	50mm/min	53	MPa	DIN EN ISO 527-2	(3) Specimen 10x10x10mm (4) Specimen 10x10x50mm, modulus range between 0.5 and 1% compression.
Forlængelse ved brud	50mm/min	13	%	DIN EN ISO 527-2	(5) For Charpy test: support span 64mm, norm specimen. n.b. = not broken
Brudforlængelse	50mm/min	58	%	DIN EN ISO 527-2	
Bøjningsstyrke	2mm/min, 10 N	73	MPa	DIN EN ISO 178	2)
Elasticitetsmodul (flexural test)	2mm/min, 10 N	2200	MPa	DIN EN ISO 178	
Kompressionsstyrke	1% / 2% / 5% 5mm/min, 10 N	14/26/53	MPa	EN ISO 604	3)
Kompressionsmodul	5mm/min, 10 N	2100	MPa	EN ISO 604	4)
Slagstyrke (Charpy)	max. 7,5J	n.b.	kJ/m ²	DIN EN ISO 179-1eU	5)
Slagstyrke med kærnv (Charpy)	max. 7,5J	16	kJ/m ²	DIN EN ISO 179-1eA	
Shore hårdhed	D	77		DIN EN ISO 868	
Termiske egenskaber	parameter	værdi	enhed	norm	kommentar
Glasovergangstemperatur		53	°C	DIN EN ISO 11357	1)
Smeltetemperatur		216	°C	DIN EN ISO 11357	
Service temperatur	short term	160	°C		2)
Service temperatur	long term	95	°C		
Termisk udvidelse (CLTE)	23-60°C, long.	13	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2	
Termisk udvidelse (CLTE)	23-100°C, long.	13	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2	
Specifik varme		1.7	J/(g*K)	ISO 22007-4:2008	
Termisk ledeevne		0.32	W/(K*m)	ISO 22007-4:2008	
Elektriske egenskaber	parameter	værdi	enhed	norm	kommentar
Specifik overflademodstand		10 ¹⁴	Ω	-	
Specifik volumen resistens		10 ¹⁴	Ω*cm	-	
Andre egenskaber	parameter	værdi	enhed	norm	kommentar
Vandabsorption	24h / 96h (23°C)	0.6 / 1.2	%	DIN EN ISO 62	1) (1) Ø ca. 50mm, h=13mm
Resistens overfor hedt vand / baser		(+)		-	2) (2) (+) limited resistance
Resistens overfor vejrpåvirkning		-		-	3) (3) - poor resistance
Brandbarhed (UL94)	corresponding to	HB		DIN IEC 60695-11-10;	4) (4) Corresponding means no listing at UL (yellow card). The information might be taken from resin, stock shape or estimation. Individual testing regarding application conditions is mandatory.