

TECASINT 5511 SD light-brown - Stock Shapes (rods, plates, tubes)

Chemical Designation

PI (Polyimide)

Colour

brown

Density

1.65 g/cm³

Fillers

glass fibres

Main features

- electrically static dissipative
- high thermal and mechanical capacity
- low thermal expansion
- high creep resistance
- resistance against high energy radiation

Target Industries

- electronics
- semiconductor technology
- cryogenic engineering
- electrical engineering
- mechanical engineering
- nuclear and vacuum technology

Mechanical properties	parameter	value	unit	norm	comment
Tensile strength	50 mm/min, 23°C	97	MPa	DIN EN ISO 527-1	
Modulus of elasticity (tensile test)	1 mm/min, 23°C	5600	MPa	DIN EN ISO 527-1	
Elongation at break (tensile test)	50 mm/min, 23°C	2,1	%	DIN EN ISO 527-1	
Flexural strength	10 mm/min, 23°C	128	MPa	DIN EN ISO 178	
Modulus of elasticity (flexural test)	2 mm/min, 23°C	5588	MPa	DIN EN ISO 178	
Elongation at break (flexural test)	10 mm/min, 23°C	2,3	%	DIN EN ISO 178	
Compression strength	10 mm/min, 23°C	254	MPa	EN ISO 604	
Compressive strain at break	10 mm/min, 23°C	21,4	%	EN ISO 604	
Compression modulus	1 mm/min	5890	MPa	EN ISO 604	
Shore hardness	Shore D, 23°C	92		DIN EN ISO 868	
Thermal properties	parameter	value	unit	norm	comment
Glass transition temperature		329	°C	DIN EN ISO 11357	(1) Found in public sources. Individual testing regarding application conditions is mandatory.
Service temperature	lower operating temperature	- 20	°C	-	1)
Service temperature	short-term	300	°C	-	2)
Service temperature	long-term	250	°C	-	3)
Thermal expansion (CLTE)	23-100°C	32	10 ⁻⁶ K ⁻¹	DIN EN ISO 11359-1;2	4)
Thermal expansion (CLTE)	100-150°C	35	10 ⁻⁶ K ⁻¹	DIN EN ISO 11359-1;2	5)
Thermal expansion (CLTE)	50-200°C	35	10 ⁻⁶ K ⁻¹	DIN EN ISO 11359-1;2	6)
Specific heat		1,01	J/(g*K)	DIN EN 821	(4) Thermal expansion XY axis
Thermal conductivity	40°C	0,32	W/(K*m)	DIN EN 821	(5) Thermal expansion XY axis
					(6) Thermal expansion XY axis
Electrical properties	parameter	value	unit	norm	comment
surface resistance	23°C	10 ⁰⁹ - 10 ¹¹	Ω	ANSI ESD STM 11.11	
surface resistivity	23°C	10 ¹⁰ - 10 ¹²	Ω/square	ANSI ESD STM 11.11	
volume resistance	23°C	10 ⁰⁹ - 10 ¹¹	Ω	ANSI ESD STM 11.12	
volume resistivity	23°C	10 ¹⁰ - 10 ¹²	Ω*cm	ANSI ESD STM 11.12	
Other properties	parameter	value	unit	norm	comment
Water absorption	24 h in water, 23°C	0.60	%	DIN EN ISO 62	(1) Corresponding means no listing at UL (yellow card). The information might be taken from resin, stock shape or estimation. Individual testing regarding application conditions is mandatory.
Flammability (UL94)	corresponding to	V0		DIN IEC 60695-11-10;	1)

→ TECASINT 5000 series show significant water uptake. Parts have to be pre-dried before fast heating to above 200 °C (drying process: 2 h per 3 mm wall thickness at 150 °C).

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com. Technical changes reserved.

Manufactured by: Ensinger Group,
a German based plastic manufacturer

Represented by:
Ensinger Asia Holding Pte Ltd.
(Singapore Branch)
for Southeast Asia

63 Hillview Avenue #02-03
Lam Soon Industrial Building
Singapore 669569
Tel +65 65524177
Fax +65 65525177
www.ensingerplastics.com/en-sg/

Date: 2023/08/14

Version: AD