

TECASINT 6062 black - Direct Forming

Chemical Designation

PI (Polyimide)

Colour

black

Density

1.51 g/cm³

Fillers

graphite, PTFE

Production process: direct forming

Main features

- excellent slip-stick properties
- very good slide and wear properties
- resistance against high energy radiation
- good chemical resistance
- sensitive to hydrolysis in higher thermal range

Target Industries

- mechanical engineering
- automotive industry
- aircraft and aerospace technology

<i>Mechanical properties</i>	<i>parameter</i>	<i>value</i>	<i>unit</i>	<i>norm</i>	<i>comment</i>
Tensile strength	50 mm/min	50	MPa	DIN EN ISO 527-1	
Modulus of elasticity (tensile test)	1 mm/min	4100	MPa	DIN EN ISO 527-1	
Elongation at break (tensile test)	50 mm/min	2.1	%	DIN EN ISO 527-1	
Flexural strength	10 mm/min	75	MPa	DIN EN ISO 178	
Modulus of elasticity (flexural test)	2 mm/min	4200	MPa	DIN EN ISO 178	
Elongation at break (flexural test)	10 mm/min	2.3	%	DIN EN ISO 178	
Compression strength	10 mm/min	125	MPa	EN ISO 604	
Compression strength	10mm/min, 10% strain	120	MPa	EN ISO 604	
Compressive strain at break	10 mm/min	17	%	EN ISO 604	
Shore hardness	Shore D	82		DIN EN ISO 868	
<i>Thermal properties</i>	<i>parameter</i>	<i>value</i>	<i>unit</i>	<i>norm</i>	<i>comment</i>
Glass transition temperature		286	°C	-	1) (1) DMA, maximum loss factor tan d
Thermal expansion (CLTE)	50-200°C	2.2 / -	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2	2) (2) Thermal expansion XYZ axis
Thermal expansion (CLTE)	200-300°C	5.8 / -	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2	3) (3) Thermal expansion XYZ axis
<i>Other properties</i>	<i>parameter</i>	<i>value</i>	<i>unit</i>	<i>norm</i>	<i>comment</i>
Water absorption	24 h in water, 23°C	0.2	%	DIN EN ISO 62	(1) Corresponding means no listing at UL (yellow card). The information might be taken from resin, stock shape or estimation. Individual testing regarding application conditions is mandatory.
Flammability (UL94)	corresponding to	V0		DIN IEC 60695-11-10;	1)

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com. Technical changes reserved.

Ensinger Sintimid GmbH
Ensingerplatz 1,
4863 Seewalchen, Austria

Tel: +43 7662 88788 0
Telefax: +43 (0) 76 62 88788-171
tecasint@ensingerplastics.com
www.ensingerplastics.com

Date: 2022/03/25

Version: AC