

TECATEC PC CW50 PL V01 natural - Composite Materials

Chemical Designation

PC (Polycarbonate)

Colour

natural

Density

1.52 g/cm³

Fillers

carbon fibres

Main features

- high dimensional stability
- good surface appearance
- low coefficient of thermal expansion
- very high stiffness
- very high strength

Target Industries

- automotive industry
- mechanical engineering
- safety engineering
- sporting goods

General material information	parameter	value	unit	norm	comment
Fibre type		carbon HT 3k		-	
Fibre architecture		twill 2/2		-	
Fibre areal weight		200	g/m ²	-	
Fibre volume content		50	%	-	
Resin weight content		38.8	%	-	
Areal weight finished product		327	g/m ²	-	
Material widths		625x525	mm	others on request	
thickness		1-95	mm	-	
Fibre orientation		0-90°		others on request	
Mechanical properties	parameter	value	unit	norm	comment
Tensile strength		440	MPa	ISO 527-4	
Modulus of elasticity (tensile test)		48000	MPa	ISO 527-4	
Flexural strength		615	MPa	ISO 14125	
Modulus of elasticity (flexural test)		48000	MPa	ISO 14125	
Compression strength		215	MPa	ISO 14126	
Compression modulus		26000	MPa	ISO 14126	
Interlaminar shear strength		44	MPa	ISO 14130	
Thermal properties	parameter	value	unit	norm	comment
Glass transition temperature		143	°C	-	(1) approximate value
Service temperature	short term	140	°C	-	
Service temperature	long term	120	°C	-	
Thermal expansion (CLTE)	in 0° and 90° direction	5	10 ⁻⁶ K ⁻¹	-	1)
Predrying	parameter	value	unit	norm	comment
Drying temperature		120	°C	-	
Drying time		3	h	-	

Nothing contained in this Technical Datasheet shall be interpreted as any express warranty or guarantee. We are neither liable for any values nor content of this datasheet. This exclusion of liability does not apply to claims for damages based on intent, gross negligence or culpable breach of material contractual obligations (cardinal obligations), nor in the case of injury to life, body or health and in the case of product liability as provided by law. Nothing contained herein shall be construed to indicate the non-existence of any relevant patents or to constitute a permission, encouragement or recommendation to practice any development covered by any patents, without permission of the owner of this patent. Data sheet parameters are subject to regular review, the current versions can be found at www.ensingerplastics.com

Manufactured by: Ensinger Group,
a German based plastic manufacturer

Represented by:
Ensinger Asia Holding Pte Ltd.
(Singapore Branch)
for Southeast Asia

63 Hillview Avenue #02-03
Lam Soon Industrial Building
Singapore 669569
Tel +65 65524177
Fax +65 65525177
www.ensingerplastics.com/en-sg/

Date: 2023/06/02

Version: AD