

# TECATEC PEEK CF50 T200 CP/IP/OS V01 natural - Composite Materials

## Chemical Designation

PEEK (Polyetheretherketone)

## Colour

natural

## Density

1.52 g/cm<sup>3</sup>

## Fillers

carbon fibres

## Main features

- excellent chemical resistance
- low coefficient of thermal expansion
- continuous service temperature up to 260 °C
- very high stiffness
- very high strength

## Target Industries

- automotive industry
- mechanical engineering
- oil and gas industry
- safety engineering
- sporting goods

The material is in the phase of further development. The characteristic values of this product may change.

General material information	parameter	value	unit	norm	comment
Fibre type		carbon HT 3k		-	
Fibre architecture		Twill 2/2		-	
Fibre areal weight		200	g/m <sup>2</sup>	-	
Fibre volume content		50	%	-	
Resin weight content		41.9	%	-	
Areal weight finished product		344	g/m <sup>2</sup>	-	
Material widths		1000 1270	mm	-	
ply thickness (consolidated)		0.22	mm	-	
Mechanical properties	parameter	value	unit	norm	comment
Tensile strength		713	MPa	ISO 527-4	
Modulus of elasticity (tensile test)		59000	MPa	ISO 527-4	
Flexural strength		866	MPa	ISO 14125	
Modulus of elasticity (flexural test)		55000	MPa	ISO 14125	
Compression strength		645	MPa	ISO 14126	
Impact strength (Charpy)		65.5	kJ/m <sup>2</sup>	-	
Interplanar shear strength		137	MPa	ISO 14129	
Interlaminar shear strength		65	MPa	ISO 14130	
Thermal properties	parameter	value	unit	norm	comment
Glass transition temperature		143	°C	-	(1) approximate value
Melting temperature		343	°C	-	
Service temperature	short term	300	°C	-	
Service temperature	long term	260	°C	-	
Thermal expansion (CLTE)	in 0° and 90° direction	5	10 <sup>-6</sup> K <sup>-1</sup>	-	1)
Predrying	parameter	value	unit	norm	comment
Drying temperature		150	°C	-	
Drying time		3	h	-	

Nothing contained in this Technical Datasheet shall be interpreted as any express warranty or guarantee. We are neither liable for any values nor content of this datasheet. This exclusion of liability does not apply to claims for damages based on intent, gross negligence or culpable breach of material contractual obligations (cardinal obligations), nor in the case of injury to life, body or health and in the case of product liability as provided by law. Nothing contained herein shall be construed to indicate the non-existence of any relevant patents or to constitute a permission, encouragement or recommendation to practice any development covered by any patents, without permission of the owner of this patent. Data sheet parameters are subject to regular review, the current versions can be found at [www.ensingerplastics.com](http://www.ensingerplastics.com)