

## TECATEC PPS CW50 PL V01 natural - Composite Materials

### Kemisk beteckning

PPS (Polyphenylen sulfide)

### Färg

Natur

### Densitet

1.52 g/cm<sup>3</sup>

### Fillers

kol fibrer

### Huvud egenskaper

- utmärkt kemisk resistans
- inneboende flambeständighet
- utmärkta mekaniska egenskaper

### Målindustrier

- bilindustrin
- maskinteknik
- olje- och gasindustrin
- säkerhetsteknik
- sporting goods

The material is in the phase of further development. The characteristic values of this product may change.

General material information	parameter	värde	enhet	norm	anmärkning
Fibre type		Carbon HT 3k		-	
Fibre architecture		Twill 2/2		-	
Fibre areal weight		200	g/m <sup>2</sup>	-	
Fibre volume content		50	%	-	
Resin weight content		42.7	%	-	
Areal weight finished product		349	g/m <sup>2</sup>	-	
Material widths		625x525	mm	others on request	
thickness		1-95	mm	-	
Fibre orientation		0-90°		others on request	
Mekaniska Egenskaper	parameter	värde	enhet	norm	anmärkning
Draghållfasthet		680	MPa	ISO 527-4	
Elasticitetsmodul (dragprov)		55000	MPa	ISO 527-4	
Böjhållfasthet		780	MPa	ISO 14125	
Elasticitetsmodul (böjningstest)		57000	MPa	ISO 14125	
Kompressionsstyrka		650	MPa	ISO 14126	
Kompressionsmodul		51000	MPa	ISO 14126	
Interplanar shear strength		131	MPa	ISO 14129	
Värmeledningsförmåga	parameter	värde	enhet	norm	anmärkning
Glasövergångstemperatur		90	°C	-	(1) approximate value
Smält temperatur		285	°C	-	
Service temperatur	short term	260	°C	-	
Service temperatur	long term	230	°C	-	
termisk expansion	in 0° and 90° direction	5	10 <sup>-6</sup> K <sup>-1</sup>	-	1)
Förtorkning	parameter	värde	enhet	norm	anmärkning
Torktemperatur		150	°C	-	
Torktid		2-3	h	-	

Nothing contained in this Technical Datasheet shall be interpreted as any express warranty or guarantee. We are neither liable for any values nor content of this datasheet. This exclusion of liability does not apply to claims for damages based on intent, gross negligence or culpable breach of material contractual obligations (cardinal obligations), nor in the case of injury to life, body or health and in the case of product liability as provided by law. Nothing contained herein shall be construed to indicate the non-existence of any relevant patents or to constitute a permission, encouragement or recommendation to practice any development covered by any patents, without permission of the owner of this patent. Data sheet parameters are subject to regular review, the current versions can be found at [www.ensingerplastics.com](http://www.ensingerplastics.com)