

TECATRON CMP natural - Stock Shapes (rods, plates, tubes)

Chemical Designation

PPS (Polyphenylsulfide)

Colour

beige opaque

Density

1.36 g/cm³

Main features

- good heat deflection temperature
- good chemical resistance
- resistance against high energy radiation
- high strength
- high dimensional stability
- high stiffness
- high creep resistance

Target Industries

- semiconductor technology

<i>Mechanical properties</i>	<i>condition</i>	<i>value</i>	<i>unit</i>	<i>test method</i>	<i>comment</i>
Tensile strength	@73°F	13,980	psi	ASTM D 638	
Modulus of elasticity (tensile test)	@73°F	673,400	psi	ASTM D 638	
Tensile strength at break	@73°F	13,920	psi	ASTM D 638	
Elongation at break (tensile test)	@73°F	4.2	%	ASTM D 638	
Flexural strength	@73°F	22,040	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@73°F	636,000	psi	ASTM D 790	
Compression strength	@ 10% strain	5,500	psi	ASTM D 695	
Compression strength	@ 1% strain	19,960	psi	ASTM D 695	
Compression modulus		484,200	psi	ASTM D 695	
Impact strength (Izod)	@73°F	0.55	ft-lbs/in	ASTM D 256	
Rockwell hardness	M scale	103.3		ASTM D 785	
<i>Thermal properties</i>	<i>condition</i>	<i>value</i>	<i>unit</i>	<i>test method</i>	<i>comment</i>
Glass transition temperature		194	°F	DIN EN ISO 11357	1) (1) Found in public sources.
Melting temperature		536	°F	DIN EN ISO 11357	2) (2) Public source injection molding data
Deflection temperature	@ 264 psi	239	°F	ISO-R 75 Method A	3) (3) Public Source Injection molding data
Deflection temperature	@ 65 psi	320	°F	ISO-R 75 Method B	4) (4) Public Source Injection molding data
Service temperature	short term	500	°F	-	5) (5) Found in public sources.
Service temperature	long term	446	°F	-	Individual testing regarding application conditions is recommended.
Thermal expansion (CLTE)		2.8	*10 ⁻⁵ in/in/°F	ASTM E 831	6) (6) Public Source Injection molding data
<i>Electrical properties</i>	<i>condition</i>	<i>value</i>	<i>unit</i>	<i>test method</i>	<i>comment</i>
Dissipation factor	@ 1 MHz	0.0011		DIN IEC 60250	1) (1) Public source injection molding data
Dielectric constant	@ 1 kHz	2.8		DIN IEC 60250	2) (2) Public source injection molding data
Dielectric constant	@ 1 MHz	4.6		DIN IEC 60250	3) (3) Public source injection molding data
<i>Other properties</i>	<i>condition</i>	<i>value</i>	<i>unit</i>	<i>test method</i>	<i>comment</i>
Water absorption	@ 24 hrs	0.02	%	ASTM D 570	(1) + good resistance
Resistance to hot water/ bases		+		-	(2) - poor resistance
Resistance to weathering		-		-	(3) Corresponding means no listing at UL (yellow card). The information might be taken from resin, stock shape or estimation. Individual testing regarding application conditions is recommended.
Flammability (UL94)	@ 3 mm	V0		-	(3)

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.