

TECATRON® PPS natural - Stock Shapes (rods, plates, tubes)

Chemical Designation

PPS (Polyphenylsulfide)

Colour

natural

Density

1.36 g/cm³

Main features

- high purity
- very good chemical resistance
- good heat deflection temperature
- high creep resistance
- high strength
- high dimensional stability
- resistance against high energy radiation

Target Industries

- chemical technology
- mechanical engineering
- precision engineering
- electrical engineering
- food processing
- food engineering
- vacuum technology

Mechanical properties	condition	value	unit	test method	comment
Modulus of elasticity (tensile test)	@ 73 °F	836,700	psi	ASTM D 638	
Tensile strength at yield	@ 73 °F	13,700	psi	ASTM D 638	
Elongation at break (tensile test)	@ 73 °F	2.5	%	ASTM D 638	
Flexural strength	@ 73 °F	20,400	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F	631,100	psi	ASTM D 790	
Compression strength	@ 10% strain	19,000	psi	ASTM D 695	
Compression modulus		400,000	psi	ASTM D 695	
Impact strength (Izod)	@ 73 °F	0.62	ft-lbs/in	ASTM D 256	
Rockwell hardness	@ 73 °F M Scale	105		ASTM D 785	
Rockwell hardness	R Scale	124		ASTM D 785	
Coefficient of friction	Dynamic, 40 psi, 50 fpm	0.24		ASTM D 3702	
Wear (K) factor	Against Steel, 40 psi, 50 fpm	540*10 ⁻¹⁰	in ³ -min/ft-lbs-hr	ASTM D 3702	
Thermal properties	condition	value	unit	test method	comment
Melting temperature		536	°F	-	(1) per UL746B
Deflection temperature	@264 psi	220	°F	ASTM D 648	(2) data from public sources
Deflection temperature	@ 66 psi	400	°F	ASTM D 648	(3) data from public sources
Service temperature	Long Term	338	°F	-	(4) data from public sources
Service temperature	Intermittent	500	°F	-	1)
Thermal expansion (CLTE)	72 F - 140 F	3.3	*10 ⁻⁵ in/in/°F	ASTM D 696	2)
Specific heat		0.239	BTU/lb-F°	ISO 22007-4:2008	3)
Thermal conductivity		2.08	BTU-in/hr-ft ² -°F	ISO 22007-4:2008	4)
Electrical properties	condition	value	unit	test method	comment
surface resistivity		1.0*10 ¹⁵	Ω/square	DIN IEC 60093	1) (1) data from public sources
Dielectric strength		450	V/mil	ASTM D 149	2) (2) data from public sources
Dissipation factor	@ 1 KHz, 73 °F	.0001		ASTM D 150	3) (3) data from public sources
Dielectric constant	@ 1 KHz, 73 °F, 50% RH	3.0		ASTM D 150	4) (4) data from public sources
Other properties	condition	value	unit	test method	comment
Moisture absorption	@ 24 hrs, 73 °F	0.01	%	ASTM D 570	(1) Estimated
Flammability (UL94)		V0		DIN IEC 60695-11-10;	1)

→ Resin specification:
ASTM D 6358-06 PPS000B00000
Shapes specification:
NONE

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.